



JOLYWOOD

385W





IEC61215(2016), IEC61730(2016) | ISO9001:2015: Quality Management System | ISO14001:2015: Environment Management System ISO45001:2018: Occupational health and safety management systems | IEC62941: 2019: Quality system for PV module manufacturing



10-30% Additional Power Generation

30 years lifespan brings 10-30% additional power generation comparing with conventional P-type module



ZERO LID (Light Induced Degradation)

N-type solar cell has no LID naturally which can increase power generation



Higher Reliability

Adpoted Jolywood lastest J-TOPCon2.0 technology, No polysilicon wrap around, Full electrical isolation, Zero leakage current; Much Safer for roof



Jolywood Delivers Reliable Performance Over Time

- Leader of N-type bifacial manufacturer
- Full-automatic facility and industry-leading technology
- · Best-in-class durability and reliability
- BNEF Tier One



Better Weak Illumination Response

Higher power output even under low-light environments like on cloudy or foggy days



Better Temperature Coefficient


Higher power generation under working conditions, thanks to passivating contact cell technology



Outstanding visual appearance

Designed with aesthetics in mind, thinner wires that appear all black at a distance

Linear Performance Warranty



*Subject to the terms and conditions contained in the applicable Jolywood Solar Limited Warranty Statement. Also this 25
-year limited product warranty is available only for products installed and operating on residential rooftops in certain regions









Electrical Properties	STC*				
Testing Condition	Front Side				
Peak Power (Pmax) (W)	365	370	375	380	385
MPP Voltage (Vmp) (V)	34.3	34.5	34.7	34.9	35.1
MPP Current (Imp) (A)	10.65	10.73	10.81	10.89	10.97
Open Circuit Voltage (Voc) (V)	41.2	41.4	41.6	41.8	42.0
Short Circuit Current (Isc) (A)	11.27	11.36	11.45	11.54	11.62
Module Efficiency (%)	20.01	20.28	20.55	20.83	21.10

*STC: Irradiance 1000 W/m², Cell Temperature 25°C, AM1.5
The data above is for reference only and the actual data is in accordance with the pratical testing Power Measurement Tolerance ±3%

Electrical Properties	NOCT*				
Testing Condition	Front Side				
Peak Power (Pmax) (W)	277	280	284	288	292
MPP Voltage (Vmp) (V)	32.2	32.4	32.6	32.8	33.0
MPP Current (Imp) (A)	8.59	8.65	8.72	8.78	8.84
Open Circuit Voltage (Voc) (V)	39.4	39.6	39.8	40.0	40.1
Short Circuit Current (Isc) (A)	9.09	9.16	9.23	9.30	9.37

*NOCT: Irradiance 800 W/m², Ambient Temperature 20°C, Wind Speed 1 m/s

Operating Properties Operating Temperature (°C) -40°C~+85°C Maximum System Voltage (V) 1500V DC (IEC) Maximum Series Fuse Rating (A) 25 Power Tolerance 0~+5W Bifaciality* 80% *Bifaciality=Pmaxrear (STC) /Pmaxfront (STC) , Bifaciality tolerance:±5%

Temperature Coefficient		
Temperature Coefficient of Pmax*	-0.300%/°C	
Temperature Coefficient of Voc	-0.250%/°C	
Temperature Coefficient of Isc	+0.045%/°C	
Nominal Operating Cell Temperature (NOCT)	42±2℃	


^{*}Temperature Coefficient of Pmax±0.03%/°C

Mechanical Properties	
Cell Size	166.00mm*83.00mm
Number of Cells	120pcs(12*10)
Module Dimension	1756mm*1039mm*30mm
Weight	23kg
Front / Rear Glass*	2.0mm/2.0mm
Frame	Anodized Aluminium Alloy
Junction Box	IP68 (3 diodes)
Length of Cable	4.0mm², +300mm/-180mm (Cable length can be customized)


*Heat strengthened glass

Peak Power MPP Voltage MPP Current Open Circuit Voltage Short Circuit Current Power Gain (Pmax) (W) (Vmp) (V) (Imp) (A) (Voc) (V) (Isc) (A) (%) 12.44 10 410 1175 41.8 34 9 15 426 34.9 12.18 41.8 12.89 20 441 35.0 12.61 41.9 13.34 41.9 25 456 35.0 13.04 13.79 30 471 35.0 41.9 14.24 13.47

Engineering Drawing (unit: mm



Characteristic Curves | HD120N-380



Packaging Con	figuration		
Packing Type	20'GP	40'GP	40'HQ
Piece/Pallet		36	
Pallet/Container	6	13	26
Piece/Container	216	468	936

*The specification and key features described in this datasheet may deviate slightly and are not guaranteed. Due to ongoing innovation, R&D enhancement, Jolywood (Taizhou) Solar Technology Co., Ltd., reserves the right to make any adjustment to the information described herein at any time without notice. Please always obtain the most recent version of the datasheet which shall be duly incorporated into the binding contract made by the parties governing all transactions related to the purchase and sale of the products described herein.



Add: No.6 Kaiyang Rd., Jiangyan Economic Development Zone, Taizhou, Jiangsu Province, China, 225500 TEL: +86 523 80612799 Email: mkt@jolywood.cn

